

Investigating the limits of resin-based luting composite photopolymerization through various thicknesses of indirect restorative materials

Hardy, C. M. F.; Bebelman, S.; Leloup, G.; Hadis, M. A.; Palin, W. M.; Leprince, J. G.

DOI:

[10.1016/j.dental.2018.05.009](https://doi.org/10.1016/j.dental.2018.05.009)

License:

Creative Commons: Attribution-NonCommercial-NoDerivs (CC BY-NC-ND)

Document Version

Peer reviewed version

Citation for published version (Harvard):

Hardy, CMF, Bebelman, S, Leloup, G, Hadis, MA, Palin, WM & Leprince, JG 2018, 'Investigating the limits of resin-based luting composite photopolymerization through various thicknesses of indirect restorative materials', *Dental Materials*, vol. 34, no. 9, pp. 1278-1288. <https://doi.org/10.1016/j.dental.2018.05.009>

[Link to publication on Research at Birmingham portal](#)

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.

Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.

Investigating the limits of resin-based luting composite photopolymerization through various thicknesses of indirect restorative materials

C.M.F. Hardy^{a, b, c, *}

chloe.hardy@uclouvain.be

S. Bebelman^c

G. Leloup^{a, b, c, d}

M.A. Hadis^e

W.M. Palin^e

J.G. Leprince^{a, b, c, d}

^aSchool of Dental Medicine and Stomatology, Université catholique (Please change all the "a" line to "School of Dental Medicine and Stomatology, at Cliniques Universitaires Saint-Luc, Universite catholique de Louvain, Belgium")de Louvain, Belgium

^bAdvanced Drug Delivery and Biomaterials (ADDB), Louvain Drug Research Institute (LDRI), Université catholique de Louvain, Brussels, Belgium

^cBio- and Soft- Matter (BSMA), Institute of Condensed Matter and Nanoscience (IMCN), Université catholique de Louvain, Louvain-la-Neuve, Belgium

^dCRIBIO (Center for Research and Engineering on Biomaterials), Brussels, Belgium

^eBiomaterials Unit, University of Birmingham, College of Medical and Dental Sciences, Institute of Clinical Sciences, School of Dentistry, 5 Mill Pool Way, Birmingham B5 7EG, UK

*Corresponding author at: School of Dental Medicine and Stomatology, Université catholique de Louvain, Belgium.

Abstract

Objective

To determine the limitations of using light-curable resin-based luting composites (RBLCs) to bond indirect ceramic/resin-composite restorations by measuring light transmittance through indirect restorative materials and the resulting degree of conversion (DC) of the luting-composites placed underneath.

Methods

Various thicknesses (0–4 mm) and shades of LAVA Zirconia and LAVA Ultimate were prepared and used as light curing filters. A commercial, light curable RBLC, RelyX Veneer (control) was compared with four experimental RBLCs of the following composition: TEGDMA/BisGMA (50/50 or 30/70 wt%, respectively); camphorquinone/amine (0.2/0.8 wt%) or Lucirin-TPO (0.42 wt%); microfillers (55 wt%) and nanofillers (10 wt%). RBLCs covered with the LAVA filter were light-cured for 40 s, either with the dual-peak BluephaseG2 or an experimental device emitting either in the blue or violet visible band. The samples were analyzed by Raman spectroscopy to determine DC. Light transmittance through the filters was measured using a common spectroscopy technique.

Results

All the factors studied significantly influenced DC ($p \leq 0.05$). RBLCs with increased TEGDMA content exhibited higher DC. Only small differences were observed comparing DC without filters and filters ≤ 1 mm ($p \geq 0.05$). For thicknesses ≥ 2 mm, significant reductions in DC were observed ($p < 0.05$). Transmittance values revealed higher filter absorption at 400 nm than 470 nm. A minimal threshold of irradiance measured through the filters that maintained optimal DC following 40 s irradiation was identified for each RBLC formulation, and ranged between 250–500 mW/cm².

Significance

This work confirmed that optimal photopolymerization of RBLCs through indirect restorative materials (≤ 4 mm) and irradiation time of 40 s is possible, but only in some specific conditions. The determination of such conditions is likely to be key to clinical success, and all the factors need to be optimized accordingly.

1 Introduction

Clinical studies describe high performance of bonded ceramic restorations (esthetics, good survival rate), not only to restore anterior teeth [1-4], but also for extensive posterior restorations [5-7]. For both indications, the bonding quality is essential to provide clinical effectiveness, especially for partial restorations. Weaknesses in the bonding interface may lead to early clinical failures; mainly loss or fracture of the restoration, but also possibly favor the occurrence of other issues such as secondary caries, post-operative sensitivity or marginal discolouration due to marginal leakage [8].

Traditionally, a dual-cure resin-based luting composite (RBLC) is preferred for the placement of indirect restorations, to ensure effective polymerization even through thick and/or opaque restorations. The dual-cure chemistry supposedly combines the assurance of ‘dark’ chemical curing with some of the numerous advantages provided by purely light-curable systems. The latter notably include improved handling aspects, such as a single paste without the need for mixing, better control of working time, faster setting, easier excess removal or improvement of the interface colour stability [9]. Despite these advantages, very few works investigated the use of purely light-curable composites to lute indirect restorations [10,11]. One reported the possibility to reach an “adequate” polymerization of a conventional resin composite (described as 80% of the maximum material microhardness) when light cured through 7.5 mm thick ‘endocrowns’ [11]. Another revealed higher bond strength values when light curable resin composites were used to lute 4 mm thick inlays compared with the use of a dual-cure resin composite [10]. Such observations may be explained by two major elements: firstly, light curable resin composites usually contain more fillers than dual cure resin cements [12], hence higher intrinsic mechanical properties [10]. Secondly, photopolymerization processes probably generate a higher concentration of free radicals, which can be profitable during the autoacceleration step in dimethacrylate resins. During such step, any new growth centre created indeed leads to efficient chain propagation since the low mobility of the building polymer chains reduces the likelihood of bimolecular termination [13]. This reinforces the potential interest of utilizing solely light-curable chemistries not only to lute veneers [14] or thin inlays, but also thicker posterior restorations, such as endocrowns [10,11]. The importance of effective photopolymerization in light-curable RBLCs, and even those systems that include autopolymerization chemistries, is highlighted in numerous works [15-18]. For example, a previous study has reported a three-fold decrease in microhardness of dual-cure RBLCs when light cured through thick (4 mm), compared with thinner (2 mm or less), or no use of indirect ceramic filters [15]. A similar observation was made when measuring the degree of conversion of a dual-cure RBLC, with a two- to four-fold decrease of conversion through opaque 2 mm ceramic filters [17]. The autopolymerization step in a dual-cured system seems therefore insufficient to ensure optimal polymerization of luting composites. Hence, undercuring of dual-cure materials beneath thick indirect restorations remains a risk, which is potentially worsened with systems that use light-curable chemistries alone. Effective polymerization of the latter, is indeed necessary to ensure optimal physico-mechanical properties [13,19] and colour stability [20,21], thereby reducing the risk of interfacial failure.

Light transmittance through a tooth-coloured indirect restoration is significantly affected by material type. Veneers are commonly fabricated with feldspathic glass (porcelain), which exhibit relatively high translucency, however, more opaque materials exist, especially those fabricated using more modern CAD/CAM processes, including resin-based composites, particle reinforced ceramic composites (e.g. lithium disilicates and leucite-based ceramics) and polycrystalline ceramics (e.g. alumina and zirconia), the latter of which are expected to be the least translucent (notwithstanding modern attempts to increase translucency of monolithic polycrystalline crowns by adjusting the phase stabilisation dopant, grain size, and so forth). Therefore, if light transport is limited by the opacity of the indirect material, other inherent material chemistries that circumvent the need for effective polymerization using higher irradiance is certainly worthy of consideration.

The interest of using alternative photoinitiator systems to the classical combination of camphorquinone/amine (CQ), such as Type 1 acylphosphine oxides, has been extensively described for direct restorative resin composites. Notably, higher final DC and higher mechanical properties have been reported using curing times shorter than 3 s [22-26]. This was explained by higher molar absorptivity and quantum yield efficiency [27,28], which are potentially key aspects as regards light-curing through indirect materials. Indeed, low transmittance is expected through thick indirect material layers, which explains the relatively long irradiation times that were used when luting with light-activated (non-dual cure) resin-composites (from 40 s [10] to several cycles of 90 s [11]).

Consequently, the aim of this work was to determine the limits of RBLC photopolymerization by measuring light transmittance through various thicknesses of indirect restorative materials and the resulting degree of conversion (DC) of the resin cements placed underneath. Experimental RBLCs of various monomer ratios and photoinitiator content, as well as filters of different materials and shades were considered.

2 Materials and Methods

The thickness of large indirect restorations such as overlays or endocrowns is inhomogeneous (Fig. 1A, B). In order to experimentally model such variability of thickness in a reproducible manner, various CAD/CAM blocks were used to prepare 10 mm diameter disc-shaped filters of 4 different thicknesses: 0.5, 1, 2 and 4 mm (± 0.01 mm).




Fig. 1 Example of Lava Ultimate (3M-ESPE) overlay of variable thickness (A), and the same overlay irradiated with BluePhaseG2 (Ivoclar-Vivadent) (Please add (B)); (C) experimental setup to polymerize RBL through a restorative material filter (thicknesses ranging from 0.5 to 4 mm).

alt-text: Fig. 1

The CAD/CAM blocks were made of either a polycrystalline, yttria-stabilised zirconia ceramic, LAVA-Zr (shades A3 and uncoloured Zr-A3 and Zr-U) or a resin composite block with dispersed fillers, LAVA Ultimate (shades A3 and MC2-Ult-A3 and Ult-MC2 - the latter reported as more opaque) (3M-ESPE, St Paul, MN, USA). Five RBLs were light-cured through these filters: four experimental formulations and RelyX Veneer (3M-ESPE, St Paul, MN, USA), a commercially-available light-curable RBL used as control. Experimental formulations were prepared to mimic the commercial material (Table 1). The experimental formulations contained two proportions of conventional monomers TEGDMA and BisGMA in ratios of 50/50 and 30/70 wt%, respectively. Each resin blend contained either camphorquinone/amine (0.2/0.8 wt% CQ) or Lucirin-TPO (0.42 wt% Lu-TPO) as the photoinitiator. The different components were weighed using an electronic analytical balance (AND FR-300-MKII, A&D INSTRUMENTS LIMITE, Abingdon, U.K. accuracy $\pm 100 \mu\text{g}$) and placed sequentially in opaque plastic pot to prevent light exposure. Barium glass microfillers and fumed silica nanofillers were added in amounts of 55/10 wt%, respectively. Silanated fillers were used, both for the nano- and micro-scale particles.

Table 1 Composition of resin-based composite cements.

alt-text: Table 1 (This table is incomplete. Please check the document attached to your querie to complete it.)

Resin	Fillers	Monomers	Photo initiator
RelyX Veneer (3M ESPE, St Paul, MN, USA)	Silane treated ceramic (55–65 wt%),	Silane treated silica (1–10 wt%) and BisGMA 10–20% of total weight	Titanium dioxide <1 wt%
	Silane treated silica (1–10 wt%) and	TegDMA 10–20% of total weight	Ethyl 4-dimethyl aminobenzoate (EDMAB) (<1 wt%)
	Reacted polycaprolactone polymer (1–10 wt%)	*	BisGMA 10-20% of total weightTegDMA 10-20% of total weight* Titanium Dioxide <1 wt%)Ethyl 4-Dimethyl Aminobenzoate (EDMAB) (< 1 wt%)Benzotriazol (< 1%wt)Diphenyliodonium Hexafluorophosphate (< 1 wt%)*enzotriazol (<1 wt%)
	*		Diphenyliodonium hexafluorophosphate (<1 wt%)
			*
CQ50/50	Barium glass fillers silanated (G018-186/K6, d50 = $3 \pm 1 \mu\text{m}$, Schott AG, Landshut Germany) and methacrylsilane treated fumed silica (12 nm, AEROSIL® R 7200 Aerosil 7200, Evonik Industries, Germany) in amounts of 55/10 wt% respectively.	50/50 wt% of Bis-GMA and TegDMA resin (Sigma-Aldrich)	Camphorquinone (Sigma Aldrich, CAS Number 10334-26-6) as the photoinitiator and dimethylaminoethyl methacrylate (Sigma Aldrich) as co-initiator, in the proportions of 0.2/0.8 wt%
CQ30/70		70/30 wt% of Bis-GMA and TegDMA resin (Sigma-Aldrich)	

TPO 50/50		50/50 wt% of Bis-GMA and TegDMA resin (Sigma-Aldrich)	Lucirin-TPO (TPO, from BASF) 0.42 wt% as the photoinitiator
TPO 70/30		70/30 wt% of Bis-GMA and TegDMA resin (Sigma-Aldrich)	

*-According to manufacturers informations.

Bis-GMA: Bisphenol A glycerolate dimethacrylate, CAS Number: 1565-94-2.
 TEGMA: Triethylene Glycol Dimethacrylate, CAS Number 109-16-0.

Fillers were incorporated sequentially using a dual asymmetric centrifuge (Speed mixer, FlackTek, USA) for 30 seconds at 3500 rpm for the nanofillers, and at 2500 rpm for the microfillers. The mixing procedure (rpm, time, etc.) was previously optimized in other work [25].

Light sources were either the dual-peak BluephaseG2 (BPG2, Ivoclar-Vivadent, Schaan, Liechtenstein; curing tip diameter = 10 mm; “High power”) or a light-curing device (AURA, Lumencor, USA; curing tip diameter = 6 mm) emitting either in the blue (AURABlue; 455–485 nm) or in the violet (AURAviolet; 395–415 nm); the irradiance for both spectral outputs was calibrated and set at around 1000 mW/cm². The irradiance values were measured with the Thorlabs Optical Power and Energy Meter PM100USB at 1020 mW/cm² for AURAviolet, 1030 mW/cm² for AURABlue and 1119 mW/cm² for the BPG2. The relationship between the absorption spectra of the photoinitiators (CQ and Lu-TPO) and the curing lights emission spectra were compared (Fig. 2; [24]).




Fig. 2 Emission spectrum of investigated curing lights (presented in relative irradiance, 100% being the maximum spectral irradiance), compared to the molar absorptivity of the two photoinitiators included in the investigated materials, i.e. Lu-TPO and CQ. The dotted lines refer to the left-Y-axis (Molar absorptivity) and the plain lines to the right-Y-axis (Relative irradiance).

alt-text: Fig. 2

Light transmittance was measured through the various filters using a UV-vis spectrometer (USB4000, Ocean Optics, UK; n = 3). The spectrometer was coupled to a 200 μm optical fibre and an opaline glass CC3 cosine corrector (3.9 mm diameter of collection area, Ocean Optics, UK) and calibrated with a National Institute of Standards and Technology (NIST) traceable light source (Mikropack DH2000/Ocean Optics, UK). Following calibration, the integration time was set automatically with a boxcar width of 0 and spectra average equals 1. The LAVA filters were interposed centrally between the tip of the light curing unit and the cosine corrector. The light device was fixed in a standardized position, with the surface of the tip parallel and in contact with the filter surface and the filter parallel and as close as possible to the cosine corrector. The absolute irradiance was calculated as the integral beneath the curve.

The light transmittance was measured with and without a polyester film, and the transmittance profile showed that there was no significant difference (p < 0,05).

The RBLC were placed in 1 mm thick, 5 mm diameter Teflon molds, covered on each side with a polyester film (≈0.1 mm thick), compressed between two glass slides to extrude excess, and covered by a ceramic filter through which 40 s light irradiation was performed with the light-tip parallel and in direct contact (Fig. 1C).

After photopolymerization, the samples (n = 3) were stored ‘dry’, in the dark at room temperature for one week, before being analyzed by Raman spectroscopy (DXR Raman Microscope, Thermo Scientific, Madison, WI USA) to

determine the degree of conversion (DC, in %) [29] on the upper RBLC surface (n = 3). Briefly, a frequency stabilized single mode diode laser excited the samples through a 50 \times microscope objective. The spectra were acquired in the area of 1600 cm^{-1} , using a 50 slit, a 60 s irradiation, 5 accumulations, and a grating of 400 lines/mm. The calculation of DC was based on the decrease in intensity of the peak corresponding to the methacrylate C = C group at 1640 cm^{-1} compared with an unpolymerized sample. The aromatic peak at 1610 cm^{-1} was used as the internal standard [30]. Given the small thickness of the RBLC layer (around 25 μm [31]), it was assumed that the DC measurement at the upper RBLC surface of the 1 mm thick samples was representative of the conversion of the whole RBLC layer.

Statistical analyses were performed with the JMP Pro 12 software (SAS). One-way ANOVA were performed followed by multiple comparisons with a level of significance of p = 0.05; when normal distribution of the data could not be verified, the non-parametric Wilcoxon test was used; when normality was verified, HSD Tukey’s test was used.

3 Results

An inverse logarithmic relationship was observed between transmittance and filter thickness. After logarithmic transformation of transmittance, linear correlations with correlations coefficients between 0.89 and 0.97 were observed (Fig. 3). Fig. 3 also confirms the previous affirmation that the transmittance is significantly lower for AURAviolet than for BPG2 and AURAbblue, especially for Zr-A3. Light transmittance for all the materials are relatively similar between AURAbblue and BPG2, although transmittance is generally higher for BPG2.




Fig. 3 Transmittance (Ln transformation) as a function of filter thickness, for the different lights (AURAbblue in two different wavelengths and BPG2). For all four types of filters, linear correlations were drawn, and are associated with the following correlation coefficients: AURAviolet Ult-A3 (R² = 0.97), Ult-MC2 (R² = 0.96), Zr-A3 (R² = 0.91), Zr-U (R² = 0.96); AURAbblue Ult-A3 (R² = 0.98), Ult-MC2 (R² = 0.97), Zr-A3 (R² = 0.89), Zr-U (R² = 0.92); BPG2 Ult-A3 (R² = 0.96), Ult-MC2 (R² = 0.93), Zr-A3 (R² = 0.80), Zr-U (R² = 0.90). For all transmittance data, standard deviations can be found in Table 2.

alt-text: Fig. 3

Light transmittance through the ceramic filters was significantly affected by thickness (p < 0.0001), type, shade (p = 0.0205 for LAVA-Zr) as well as by light type (p < 0.0001), but not for either shade of Ultimate (p = 0.4218) (Wilcoxon test) (representative examples in Fig. 3, full results in Table 2)

Table 2 Light transmittance depending on filter thickness, in % of maximum transmittance (without interposition of any filter)*.

alt-text: Table 2

Curing light	Filter material	0.5mm	1mm	2mm	4mm
BPG2	Ult-A3	63.54 (0.71)	47.72 (0.59)	25.17 (0.21)	13.52 (0.22)
		A a	B a	C b	D b
	Ult-MC2	62.64 (1.00)	40.60 (0.21)	22.58 (0.27)	13.28 (0.25)
		A a	B c	C c	D b
	Zr-A3	38.40 (0.52)	27.23 (0.27)	15.76 (0.31)	10.90 (0.41)
		A c	B d	C d	D c
	Zr-U	56.72 (0.14)	41.94 (1.01)	28.95 (0.41)	17.51 (0.25)
		A b	B b	C a	D a
AURABlue	Ult-A3	54.75 (1.07)	33.12 (0.31)	14.04 (0.30)	4.01 (0.39)
		A a	B a	C a	D b
	Ult-MC2	47.44 (3.61)	27.42 (0.48)	11.00 (0.30)	3.27 (0.15)
		A b	B b	C b	D c
	Zr-A3	29.04 (0.50)	16.72 (0.22)	5.72 (0.19)	2.36 (0.29)
		A d	B d	C c	D d
	Zr-U	37.41 (2.60)	24.35 (0.35)	13.65 (0.11)	4.95 (0.40)
		A c	B c	C a	D a
AURAviolet	Ult-A3	43.86 (0.31)	22.06 (0.29)	6.11 (0.62)	0.75 (0.71)
		A a	B a	C b	D b
	Ult-MC2	41.04 (2.32)	17.25 (0.29)	4.77 (0.69)	0.42 (0.57)
		A b	B c	C c	D b
	Zr-A3	4.41 (0.76)	0.33 (0.94)	**	**
		A d	B d		
	Zr-U	35.29 (0.45)	19.48 (0.40)	9.31 (0.85)	1.93 (0.39)
		A c	B b	C a	D a

*Similar upper-case letters and various shades of grey connect in the same row results which are not significantly different (based on Tuckey's test, $p = 0.05$). Lower-case letters connect in the same column (and for a given curing light) results which are not significantly different at a given filtre thickness (based on Tukey's test $p = 0.05$). **No transmittance value could be measured.

Overall, light transmittance decreased significantly ($p < 0.05$) with each additional ceramic filter thickness (Table 2). The transmittance was generally low through all 4 mm thickness filters, i.e. between 10.9 and 17.5% for BPG2, between 2.4 and 5.0% for AURABlue, and between 0.42 and 1.93 for AURAviolet (Fig. 3 and Table 2).


The comparison of light transmittance between the ceramic and resin composite of similar shade (A3) revealed a lower transmittance at each thickness for each material, respectively (purple and red curves, respectively, in Fig. 3; Table 2) for each of the curing lights.

The effect of filter shade was more obvious for LAVA-Zr, with a significantly lower transmittance through Zr-A3 than Zr-U at each thickness (purple and orange curves, respectively, in Fig. 3) and for all three lights (Table 2). For LAVA-Ult, a tendency of higher transmittance was observed for Ult-A3 as compared to Ult-MC2, but the differences were not statistically significant in all conditions (red and green curves, respectively, in Fig. 3; Table 2).

BPG2 seemed to be associated with higher percentage of transmittance than AURA for each thickness and material type. The same observation could be done for AURABlue as compared to AURAviolet, the latter yielding the lowest transmittance values (Table 2).

Regarding DC, the type of RBLC ($p = 0.0001$, Wilcoxon test), photoinitiator and monomers contents ($p < 0.0001$), filter type ($p = 0.0005$), filter shade ($p = 0.0061$ for LAVA-Zr) and light ($p < 0.0001$) as well as thickness ($p = 0.0001$) all significantly influenced the values, except for the shade of Ultimate ($p = 0.5349$) (Wilcoxon test).

Filter material	Resin composition	No filter	0.5mm	1mm	2mm	4mm
Ult-A3	CQ 50/50	67.9 (0.8)	69.17 (0.68)	69.97 (0.75)	68.13 (0.40)	58.67 (0.93)
		Ab	A b	A b	A a	B a
	CQ 70/30	58.9 (0.8)	60.63 (1.15)	61.03 (0.86)	59.00 (1.15)	49.77 (1.86)
		Ac	A c	A d	A c	B c
	TPO 50/50	74.7 (0.6)	72.27 (0.49)	74.73 (0.75)	69.87 (0.72)	53.87 (2.10)
		Aa	A a	A a	B a	C b
	TPO 70/30	67.1 (0.9)	68.20 (0.96)	66.60 (0.50)	63.20 (2.00)	41.90 (1.82)
		Ab	A b	AB c	B b	C d
	RelyX Veneer	57.2 (1.6)	55.42 (0.48)	54.34 (0.77)	54.12 (1.40)	51.32 (0.82)
		Ac	A d	AB e	AB d	B bc
Ult-MC2	CQ 50/50	67.2 (0.8)	67.18 (1.10)	68.90 (1.00)	65.54 (0.54)	53.25 (1.38)
		Ab	A b	A b	A a	B a
	CQ 70/30	58.9 (0.8)	60.28 (0.52)	60.69 (0.56)	58.00 (0.31)	45.98 (1.62)
		Ac	A c	A d	A bc	B a
	TPO 50/50	74.7 (0.6)	74.27 (1.40)	74.41 (0.98)	67.16 (0.56)	36.50 (6.88)
		Aa	A a	A a	A a	B b
	TPO 70/30	67.1 (0.9)	66.12 (0.26)	65.59 (1.70)	59.73 (2.88)	22.38 (7.88)
		Ab	A b	A c	A b	B c
	RelyX Veneer	57.2 (1.6)	54.20 (1.14)	56.77 (1.00)	55.71 (1.38)	47.84 (1.33)
		Ac	A d	A e	A c	B a
Zr-A3	CQ 50/50	67.2 (0.8)	70.03 (0.75)	69.77 (0.74)	62.57 (0.81)	33.77 (2.45)
		Ab	A a	A a	B a	C b
	CQ 70/30	58.9 (0.8)	59.93 (0.40)	59.33 (0.57)	52.57 (3.51)	25.97 (4.00)
		Ac	A b	A b	B b	C c
	TPO 50/50	74.7 (0.6)	67.67 (1.89)	54.47 (3.84)	3.90 (0.173)	0.10 (0.09)
		Aa	B a	C c	D c	D d
<div> <div></div> <div>A1</div> </div>	TPO 70/30	67.1 (0.9)	61.83 (2.35)	44.40 (0.95)	1.9 (1.85)	0.37 (0.54)
		Ab	B b	C d	D c	D d
	RelyX Veneer	57.2 (1.6)	54.88 (1.77)	55.79 (1.92)	54.01 (0.69)	41.61 (1.25)
		Ac	A c	A bc	A b	B a
Zr-U	CQ 50/50	67.2 (0.8)	65.94 (6.90)	67.74 (0.43)	66.06 (0.47)	63.15 (4.61)
		Ab	A b	A b	A b	A a
	CQ 70/30	58.9 (0.8)	59.14 (0.69)	59.55 (0.59)	58.11 (0.52)	51.94 (0.53)
		Ac	A c	A d	A d	B b
	TPO 50/50	74.7 (0.6)	74.10 (1.05)	73.34 (0.37)	71.13 (1.11)	63.23 (0.98)
		Aa	A a	AB a	B a	C a
	TPO 70/30	67.1 (0.9)	64.50 (1.34)	65.21 (0.87)	62.99 (0.47)	53.33 (0.84)
		Ab	AB bc	AB c	B c	C b
	RelyX Veneer	57.2 (1.6)	52.47 (3.04)	54.01 (0.88)	53.47 (1.60)	51.17 (0.64)
		Ac	AB d	AB e	AB e	B b

* Similar upper-case letters and various shades of grey connect in the same row results which are not significantly different (based on Tuckey’s test, p = 0.05). Lower-case letters connect in the same column results which are not significantly different at a given filtre thickness (based on Tukey’s test p = 0.05).

Annotations:

A1. Please suppress this line in the middle of the box

Table 4 Degree of conversion depending on filter thickness for AURA blue (468 nm+-10 nm)*.

alt-text: Table 4

Material filter	Resin composition	No filter	0.5mm	1mm	2mm	4mm
Ult-A3	CQ 50/50	66.7 (1.1)	65.87 (0.46)	65.93 (1.02)	62.97 (0.25)	55.77 (2.45)
		Aa	A a	A a	A a	B a
	CQ 70/30	52.5 (1.7)	55.66 (1.08)	55.48 (2.38)	52.15 (4.08)	41.29 (3.79)
		Ab	A b	A b	A b	B b
	RelyX Veneer	46.6 (4.0)	42.25 (1.45)	42.58 (0.76)	41.48 (1.88)	40.02 (3.09)
		Ac	A c	A c	A c	A b
Ult-MC2	CQ 50/50	66.7 (1.1)	68.40 (1.73)	67.87 (1.02)	62.13 (1.65)	52.97 (1.50)
		Aa	A a	A a	B a	C a
	CQ 70/30	52.5 (1.7)	55.75 (1.68)	55.87 (0.48)	48.77 (2.23)	38.48 (2.88)
		ABb	A b	A b	B b	C b
	RelyX Veneer	46.6 (4.0)	47.37 (1.10)	44.10 (0.36)	35.33 (0.45)	13.43 (5.06)
		Ab	A c	A c	B c	C c
Zr-A3	CQ 50/50	66.7 (1.1)	64.23 (0.81)	63.30 (0.87)	59.07 (0.75)	35.43 (0.70)
		Aa	AB a	B a	C a	D a
	CQ 70/30	52.5 (1.7)	55.09 (0.56)	55.50 (0.81)	49.43 (5.36)	25.97 (4.00)
		Ab	A b	A a	A b	B b
	RelyX Veneer	46.6 (4.0)	42.51 (0.95)	42.93 (6.15)	37.94 (6.77)	26.50 (0.88)
		Ac	A c	A b	A b	B b
Zr-U	CQ 50/50	66.7 (1.1)	64.20 (0.87)	63.67 (1.27)	63.43 (0.45)	58.46 (0.63)
		Aa	B a	B a	B a	C a
	CQ 70/30	52.5 (1.7)	54.68 (0.73)	50.68 (7.06)	53.45 (0.79)	47.44 (0.50)
		Ab	A b	A b	A b	A b
	RelyX Veneer	46.6 (4.0)	42.70 (1.51)	38.63 (0.76)	42.90 (1.56)	29.00 (3.96)
		Ab	B c	B c	B c	C c

*Similar upper-case letters and various shades of grey connect in the same row results which are not significantly different (based on Tuckey’s test, p = 0.05). Lower-case letters connect in the same column results which are not significantly different at a given filtre thickness (based on Student t test, p = 0.05).

Table 5 Degree of conversion depending on filter thickness for AURAviolet (400 nm+-10 nm).

alt-text: Table 5

Material Filter	Resin composition	No filter	0.5mm	1mm	2mm	4mm
Ult-A3	TPO 50/50	67.8 (0.9)	72.06 (0.36)	72.69 (0.74)	72.33 (2.15)	66.03 (1.48)
		Ba	A a	A a	A a	B a
	TPO 70/30	68.2 (0.3)	68.59 (0.28)	66.60 (0.50)	67.56 (1.05)	60.26 (2.06)
		Aa	A b	A b	A b	B b
Ult-MC2	TPO 50/50	67.8 (0.9)	72.71 (0.83)	72.18 (0.53)	71.93 (1.29)	54.29 (3.48)
		Aa	A a	A a	A a	B a
	TPO 70/30	68.2 (0.3)	69.52 (2.98)	68.62 (0.54)	65.45 (1.12)	53.41 (2.15)
		Aa	A a	A b	A b	B a
Zr-A3	TPO 50/50	67.8 (0.9)	71.81 (0.99)	66.21 (0.14)	0*	0*
		Aa	A a	A a	B a	B a
	TPO 70/30	68.2 (0.3)	64.16 (2.10)	63.91 (1.20)	2.05 (0.72)	1.76 (0.06)
		A a	A b	A b	B a	B a
Zr-U	TPO 50/50	67.8 (0.9)	71.06 (2.26)	72.65 (1.19)	72.88 (2.85)	69.00 (0.95)
		Ba	A a	A a	A a	A a
	TPO 70/30	68.2 (0.3)	67.81 (0.42)	65.53 (1.95)	65.81 (0.43)	64.18 (0.80)
		Aa	A a	A b	A b	B b

Mean degree of conversion for the light-curing unit Aura. 400 nm. expressed in percents. The results in a same raw, unconnected with the same letter are significantly different (p-value 0.05), from the test Kruskal-Wallis. Minuscule letters show significantly difference between different resin composition. within a same material (p-value 0.05. from the Student’s t-test).

*0 is not a measured value, because the DC was so low than we could not measure it.

While the effect of monomer ratio is important on the absolute DC value at a given filter thickness, DC values with increasing filter thickness and a given photoinitiator system decrease similarly for 50/50 and 70/30 ratios (Tables 3-5). Notably, the drops corresponding to significant differences can be observed at similar filter thicknesses.

Although DC without filters and with thin filters were higher for Lu-TPO-based RBLC, the trend reversed when using thick (4 mm) filters with BPG2 (Table 3). When using AURA however, where irradiance was comparable between violet and blue peaks, such differences were not observed, DC of Lu-TPO-based materials remaining higher at 4 mm, except for Zr-A3 (Tables 4 and 5).

Regarding filter type, as observed for transmittance, the comparison of DC between ceramic and resin composite filters was achieved for similar shade (A3), with a significantly lower DC for Zr-A3 than for Ult-A3 (Tables 3-5) for each of the three curing lights.

In relation to what was observed for transmittance, the effect of filter shade on DC was more obvious for LAVA-Zr, with a significantly lower DC through Zr-A3 than Zr-U and for all three lights (Tables 3-5). For Lava-Ult DC was higher through Ult-A3 than through Ult-MC2 (Tables 3-5), although differences were not statistically significant (p > 0.05).

Regarding the same shade for the two different materials, a significant difference was observed between Zr-A3 and Ult-A3 for the DC obtained through thicknesses >2 mm.

With regard to thickness, the use of filters ≤1 mm resulted in few significant differences in DC when compared with RBLCs without filters. For thicknesses ≥2 mm, more significant reductions in DC were observed, particularly at 4 mm, depending on the ceramic filter/light/photoinitiator combination. In general, the critical decrease in DC was observed between 2 and 4 mm. However, for some combinations, no significant decrease in DC was observed, even for 4 mm-thick filters (p > 0.05), i.e. Rely-X Veneer ~~AURAbblue – Ult-A3, CQ70/30~~ ~~AURAbblue – Zr-U, CQ50/50~~ ~~BPG2 – AURAbblue – Ult-A3, CQ70/30~~ ~~AURAbblue – Zr-U, CQ50/50~~ ~~BPG2 – (Please replace by: i.e. Rely-X Veneer cured by AURAbblue through Ult-A3; CQ70/30 cured by AURAbblue through Zr-U; CQ50/50 cured by BPG2 through Zr-U.)~~Zr-U (Tables 3-5).

4 Discussion

The current work confirmed that optimal photopolymerization of RBLCs through indirect restorative materials (≤4 mm) and irradiation time of 40 s is possible, but only for specific conditions. The determination of such

conditions is likely to be key to clinical success, and all the factors studied in the present work (filter material type, thickness and shade, monomer composition, photoinitiator content, etc.) significantly impacted both transmission and conversion.

The first obvious limitation of this procedure was to achieve sufficient light transmittance for optimal polymerisation of the RBLC through the indirect restoration. The significant impact of material shade on transmittance observed here confirmed the findings of previous studies, i.e. that darker shades led to lower transmittance both in ceramics and resin composites [17,32,33]. This in turn resulted in lower conversion or lower mechanical properties of RBLC [16-18].

The inverse logarithmic relationship between material thickness and transmittance described in other works [32] was confirmed here (Fig. 3), the slope being specific to each curing light/material combination. The most important decrease in transmittance observed at shorter wavelengths (AURAViolet) with the investigated materials is also in accordance with previous work [34], and may represent a limitation for these systems. However, this may be material specific and depend on each particular filler, resin composition and ratio. Nevertheless, the effects of increased violet light transmittance through indirect materials are worthy of further investigation, especially for RBLCs containing photoinitiator chemistries that absorb as shorter wavelength bands.

The second obvious limitation to light curing RBLCs through thick layers was understanding the exact definition of “sufficient” transmittance. Perhaps a sensible approach would be a light transmittance high enough (for a given irradiation time, here 40 s) in order to reach a DC comparable to that obtained without any filter. Such threshold could be identified in the current work as ranging between 250 and 500 mW/cm² (Fig. 4). Such presentation of the data avoids arduous line-by-line analysis of the data tables (Tables 3-5), which often results in conclusions that are only relevant to each combination of filter types, shades, curing lights, etc. The ability to achieve an optimal DC purely by light curing depends on the combination of irradiance and irradiation time. It has been described before that there is “no apparent lower limit to the irradiance that may give effective polymerization, at least down to 25 mW/cm²” [35]. This was reported for direct restorative composites, in thick layers (2 mm). In the context of RBLCs, where layers around 25 µm are used [31], this statement becomes even more relevant. As for the upper limit of irradiation time, it would be determined as the time a clinician is willing to devote to the light curing procedure, or risk of over-heating the pulp. Therefore, the question is not whether a light-curable RBLC can be cured optimally through thick indirect restorations, but rather, in what irradiation time (provided that a minimum irradiance reaches the material)? For the present work, this parameter was set at 40 s; other works (e.g. Ref. [36] indicated that maximum thickness for an efficient light cure during 20 s through ceramic filters is 2 mm. Therefore, it would be more appropriate to consider transmittance rather than filter material type, shade or thickness, and to adapt the irradiation time to provide specific indications for each luting material. Curing time exposure is the most critical parameter for optimizing degree of conversion.

Within the current curing parameters (40 s irradiation time), DC varied significantly with monomer ratio, photoinitiator type and curing light. Considering the monomer ratio, an increased low molecular weight monomers (TEGDMA) content led, as expected, to higher DC for RBLCs light cured under similar conditions [37,38]. This can be explained by their high molecular mobility, which enables additional propagation in the later stages of polymerization reaction, i.e. when it becomes diffusion-controlled [37,38]. Despite the attempt to formulate the experimental RBLCs in a comparable fashion to our control commercial material (Rely-X Veneer), it appeared that the optimal DC of the latter was in all cases inferior to the experimental formulations. Reasons for this may include the effect of proprietary compounds, pigments and other compounds that act as competitive absorbers, and/or a less favorable photoinitiator and co-monomer combination. Furthermore, although co-monomer ratio had an impact on the absolute DC values, it had no influence on the evolution of DC values with increasing filter thickness, which purely depends on light transmission.

Regarding the photoinitiator type, DC results confirmed previously described trends that for similar irradiance, resin composites or adhesives using Lu-TPO showed higher DC than their CQ counterparts (Fig. 4) [20,22,24,26,39,40]. Similarly, Lu-TPO-based light cured systems were associated first with a lower release of un-reacted monomers, hence with a lower cytotoxic potential [24], and second with superior mechanical properties compared to CQ-counterparts [23]. Higher mechanical properties may lead to a more effective, durable and stable bonding interface (tooth-RBLC and RBLC-indirect restorative material) over time with a reduced solubility [24], which remains to be verified.

The higher DC combined with higher mechanical properties of Lu-TPO-based composites were said to result in a higher cross-linking density, a characteristic which was also suggested to account for a higher color stability [20,41] and an improved resistance to hydrolytic degradation [20] compared with CQ-based materials. This further supports the potential of using Lu-TPO-based RBLC materials, to reduce the risk of interfacial degradation and discoloration. Such detrimental effects have been described in a greater proportion when using dual-cured materials compared with purely light cured types [9]. Other factors explaining the higher color stability may also relate to the oxidation process of the amine present in the CQ initiation system, which causes discolouration [21]. During photopolymerization, amines may also form by-products that can also cause yellow or brown discolouration [42]. The absence of amine in the catalyst system based on Lu-TPO could be associated with reduced shade alteration after aging. In summary, the use of Lu-TPO as photoinitiator in RBLCs has potential to improve clinical outcomes, both in terms of bonding efficiency, bonding stability as well as color stability. The latter is particularly important in case of thin veneers, since the final colour of these restorations after bonding to teeth were clearly shown to be influenced by the shade of the underlying structures, including the luting system [43].

Finally, the light spectrum and spectral irradiance has an important impact in terms of curing efficiency. Despite the increased transmitted irradiance of BPG2 (Fig. 3), which is probably due to the higher combined irradiance

of the two different spectrum present in the BPG2 light, DC values and profiles were similar for CQ-based materials, and higher for AURAviolet at lower irradiances (Fig. 4). This could be explained by the fact that while blue peaks between BPG2 and AURAbblue were relatively comparable, the violet peak in BPG2 corresponds to only 20% of the total irradiance (Fig. 2). This results in a lower transmittance of the (~410 nm) violet spectrum at a given BPG2 transmittance value. Moreover, the emission peak of AURAviolet was located at shorter wavelengths (~405 nm), providing a more effective overlap with Lu-TPO absorption spectrum than the violet peak of the BPG2 (Fig. 2). For the commercial product Rely-X Veneer, the higher DC results associated with BPG2 compared with AURAbblue at each level of transmittance was likely a result of the broader spectrum of the blue peak of the BPG2 compared to AURAbblue, and consequently, a larger overlap with the absorption spectrum of CQ. Another less likely explanation would be the presence of an additional photoinitiating system in Rely-X Veneer absorbing at lower wavelengths, which would then benefit from the violet emission of the BPG2.

5 Significance

The current investigation confirmed that, under specific conditions, optimal photopolymerization of RBLCs could be achieved through indirect restorative materials (≤ 4 mm) and an irradiation time of 40 s. Such an approach, which is associated with both clinical advantages and fundamental improvements in material properties, may be viable, however, multiple factors such as monomer composition, photoinitiator content, filter material and thickness (studied here), and prolonged curing time (> 40 s) should be optimized accordingly.

The Lu-TPO-based RBLC provided higher conversion compared with the traditional CQ system, provided that sufficiently high irradiance in the violet wavelength range was used.

Finally, the performance of such an approach in terms of bond strength, bond stability, and ultimately clinical efficiency should be verified.

References

- [1] M. Fradeani, M. Redemagni and M. Corrado, Porcelain laminate veneers: 6- to 12-year clinical evaluation—a retrospective study, *The International journal of periodontics & restorative dentistry* *Int J Periodontics Restorative Dent* **25** 2005, 9-17.
- [2] M. Kern, N. Passia, M. Sasse and C. Yazigi, Ten-year outcome of zirconia ceramic cantilever resin-bonded fixed dental prostheses and the influence of the reasons for missing incisors, *J Dent* **65**, 2017, 51-55.
- [3] M. Kern, Fifteen-year survival of anterior all-ceramic cantilever resin-bonded fixed dental prostheses, *J Dent* **56**, 2017, 133-135.
- [4] M. Peumans, J. De Munck, S. Fieuws, P. Lambrechts, G. Vanherle and B. Van Meerbeek, A prospective ten-year clinical trial of porcelain veneers, *The journal of adhesive dentistry* *J Adhes Dent* **6**, 2004, 65-76.
- [5] J.W. van Dijken and L. Hasselrot, A prospective 15-year evaluation of extensive dentin-enamel-bonded pressed ceramic coverages, *Dent Mater* **26**, 2010, 929-939.
- [6] J.J. Archibald, G.C. Santos, Jr. and M.J. Moraes Coelho Santos, Retrospective clinical evaluation of ceramic onlays placed by dental students, *J Prosthet Dent* 2017.
- [7] (Ref 7: J Dent Res Vol 97, Issue 2, 2018) M.B. Blatz, M. Vonderheide and J. Conejo, The Effect of Resin Bonding on Long-Term Success of High-Strength Ceramics *Journal of dental research* *effect of resin bonding on long-term success of high-strength ceramics*, *J Dent Res* 2017, <https://doi.org/10.1177/0022034517729134>.
- [8] J.L. Ferracane and T.J. Hilton, Polymerization stress—is it clinically meaningful?, *Dent Mater* **32**, 2016, 1-10.
- [9] E. Kilinc, S.A. Antonson, P.C. Hardigan and A. Kesercioglu, Resin cement color stability and its influence on the final shade of all-ceramics, *J Dent* **39** (Suppl 1), 2011, e30-e36.
- [10] A. Kameyama, K. Bonroy, C. Elsen, A.K. Luhrs, Y. Suyama, M. Peumans, et al., Luting of CAD/CAM ceramic inlays: direct composite versus dual-cure luting cement, *Bio-medical materials and engineering* *med Mater Eng* **25**, 2015 279-288.
- [11] L. Gregor, S. Bouillaguet, I. Onisor, S. Ardu, I. Krejci and G.T. Rocca, Microhardness of light- and dual-polymerizable luting resins polymerized through 7.5-mm-thick endocrowns, *J Prosthet Dent* **112**, 2014, 942-948.
- [12] N. Kramer, U. Lohbauer and R. Frankenberger, Adhesive luting of indirect restorations, *Am J Dent* **13**, 2000, 60D-76D.
- [13] J.G. Leprince, W.M. Palin, M.A. Hadis, J. Devaux and G. Leloup, Progress in dimethacrylate-based dental composite technology and curing efficiency, *Dent Mater* **29**, 2013, 139-156.
- [14] L.F. da Cunha, L.O. Pedroche, C.C. Gonzaga and A.Y. Furuse, Esthetic, occlusal, and periodontal rehabilitation of anterior teeth with minimum thickness porcelain laminate veneers, *J Prosthet Dent* **112**, 2014, 1315-1318.

- [15]** C.J. Soares, N.R. da Silva and R.B. Fonseca, Influence of the feldspathic ceramic thickness and shade on the microhardness of dual resin cement, *Oper Dent* **31**, 2006, 384-389.
- [16]** N. Ilie and R. Hickel, Correlation between ceramics translucency and polymerization efficiency through ceramics, *Dent Mater* **24**, 2008, 908-914.
- [17]** S.P. Passos, E.T. Kimpara, M.A. Bottino, G.C. Santos, Jr. and A.S. Rizkalla, Effect of ceramic shade on the degree of conversion of a dual-cure resin cement analyzed by FTIR, *Dent Mater* **29**, 2013, 317-323.
- [18]** X. Meng, K. Yoshida and M. Atsuta, Influence of ceramic thickness on mechanical properties and polymer structure of dual-cured resin luting agents, *Dent Mater* **24**, 2008, 594-599.
- [19]** J.G. Leprince, P. Leveque, B. Nysten, B. Gallez, J. Devaux and G. Leloup, New insight into the **depth of cure** "depth of cure" of dimethacrylate-based dental composites, *Dent Mater* **28**, 2012, 512-520.
- [20]** P.P. Albuquerque, A.D. Moreira, R.R. Moraes, L.M. Cavalcante and L.F. Schneider, Color stability, conversion, water sorption and solubility of dental composites formulated with different photoinitiator systems, *J Dent* **41** (Suppl 3), 2013, e67-e72.
- [21]** L.R. Archegas, A. Freire, S. Vieira, D.B. Caldas and E.M. Souza, Colour stability and opacity of resin cements and flowable composites for ceramic veneer luting after accelerated ageing, *J Dent* **39**, 2011, 804-810.
- [22]** J.G. Leprince, M. Hadis, A.C. Shortall, J.L. Ferracane, J. Devaux, G. Leloup, et al., Photoinitiator type and applicability of exposure reciprocity law in filled and unfilled photoactive resins, *Dent Mater* **27**, 2011, 157-164.
- [23]** W.M. Palin, M.A. Hadis, J.G. Leprince, G. Leloup, L. Boland, G.J. Fleming, et al., Reduced polymerization stress of MAPO-containing resin composites with increased curing speed, degree of conversion and mechanical properties, *Dent Mater* **30**, 2014, 507-516.
- [24]** L.D. Randolph, W.M. Palin, S. Bebelman, J. Devaux, B. Gallez, G. Leloup, et al., Ultra-fast light-curing resin composite with increased conversion and reduced monomer elution, *Dent Mater* **30**, 2014, 594-604.
- [25]** L.D. Randolph, W.M. Palin, D.C. Watts, M. Genet, J. Devaux, G. Leloup, et al., The effect of ultra-fast photopolymerisation of experimental composites on shrinkage stress, network formation and pulpal temperature rise *Dent Mater* **30**, 2014, 1280-1289.
- [26]** L.F. Schneider, L.M. Cavalcante, S.A. Prael, C.S. Pfeifer and J.L. Ferracane, Curing efficiency of dental resin composites formulated with camphorquinone or trimethylbenzoyl-diphenyl-phosphine oxide, *Dent Mater* **28**, 2012, 392-397.
- [27]** M.G. Neumann, W.G. Miranda, Jr., C.C. Schmitt, F.A. Rueggeberg and I.C. Correa, Molar extinction coefficients and the photon absorption efficiency of dental photoinitiators and light curing units, *J Dent* **33**, 2005, 525-532.
- [28]** M.G. Neumann, C.C. Schmitt, G.C. Ferreira and I.C. Correa, The initiating radical yields and the efficiency of polymerization for various dental photoinitiators excited by different light curing units, *Dent Mater* **22**, 2006, 576-584.
- [29]** C. Pianelli, J. Devaux, S. Bebelman and G. Leloup, The micro-Raman spectroscopy, a useful tool to determine the degree of conversion of light-activated composite resins, *J Biomed Mater Res* **48**, 1999, 675-681.
- [30]** J.G. Leprince, W.M. Palin, J. Vanacker, J. Sabbagh, J. Devaux and G. Leloup, Physico-mechanical characteristics of commercially available bulk-fill composites, *J Dent* **42**, 2014, 993-1000.
- [31]** A.R. Kious, H.W. Roberts and W.W. Brackett, Film thicknesses of recently introduced luting cements, *J Prosthet Dent* **101**, 2009, 189-192.
- [32]** L. Musanje and B.W. Darvell, Curing-light attenuation in filled-resin restorative materials, *Dent Mater* **22**, 2006, 804-817.
- [33]** R.T. Peixoto, V.M. Paulinelli, H.H. Sander, M.D. Lanza, L.A. Cury and L.T. Poletto, Light transmission through porcelain, *Dent Mater* **23**, 2007, 1363-1368.
- [34]** J.E. Harlow, F.A. Rueggeberg, D. Labrie, B. Sullivan and R.B. Price, Transmission of violet and blue light through conventional (layered) and bulk cured resin-based composites, *J Dent* **53**, 2016, 44-50.
- [35]** L. Musanje and B.W. Darvell, Polymerization of resin composite restorative materials: exposure reciprocity, *Dent Mater* **19**, 2003, 531-541.
- [36]** N. Ilie, Transmitted irradiance through ceramics: effect on the mechanical properties of a luting resin cement, *Clinical oral investigations Oral Investig* **21**, 2017, 1183-1190.
- [37]** L.D. Randolph, J. Steinhaus, B. Moginger, B. Gallez, J. Stansbury, W.M. Palin, et al., Photopolymerization of highly filled dimethacrylate-based composites using Type I or Type II photoinitiators and varying co-monomer ratios, *Dent Mater* **32**, 2016, 136-148.

- [38]** L.G. Lovell, S.M. Newman and C.N. Bowman, The effects of light intensity, temperature, and comonomer composition on the polymerization behavior of dimethacrylate dental resins, *Journal of dental research* *Dent Res* **78**, 1999, 1469-1476.
- [39]** V. Miletic and A. Santini, Micro-Raman spectroscopic analysis of the degree of conversion of composite resins containing different initiators cured by polywave or monowave LED units, *J Dent* **40**, 2012, 106-113.
- [40]** P. Pongprueksa, V. Miletic, H. Janssens, K.L. Van Landuyt, J. De Munck, L. Godderis, et al., Degree of conversion and monomer elution of CQ/amine and TPO adhesives, *Dent Mater* **30**, 2014, 695-701.
- [41]** D. Manojlovic, M.D. Dramicanin, M. Lezaja, P. Pongprueksa, B. Van Meerbeek and V. Miletic, Effect of resin and photoinitiator on color, translucency and color stability of conventional and low-shrinkage model composites, *Dent Mater* **32**, 2016, 183-191.
- [42]** N. Ilie and R. Hickel, Can CQ be completely replaced by alternative initiators in dental adhesives?, *Dent Mater J* **27**, 2008, 221-228.
- [43]** D.O. Dede, O. Sahin, O.S. Ozdemir, B. Yilmaz, E. Celik and A. Koroglu, Influence of the color of composite resin foundation and luting cement on the final color of lithium disilicate ceramic systems, *J Prosthet Dent* **117**, 2017, 138-143.

Queries and Answers

Query: “Your article is registered as a regular item and is being processed for inclusion in a regular issue of the journal. If this is NOT correct and your article belongs to a Special Issue/Collection please contact m.renaud@elsevier.com immediately prior to returning your corrections.”

Answer: ok

Query: The author names have been tagged as given names and surnames (surnames are highlighted in teal color). Please confirm if they have been identified correctly.

Answer: ok

Query: Please check the corresponding author e-mail address and correct if necessary.

Answer: Corresponding author at: chloe.hardy@uclouvain.be

Query: Please check whether the designated corresponding author is correct, and amend if necessary.

Answer: Corresponding author at: chloe.hardy@uclouvain.be

Query: Please check the address for the corresponding author and correct if necessary.

Answer: Corresponding author at: chloe.hardy@uclouvain.be

Query: As per journal specification maximum 10 keywords are allowed. Kindly provide keywords.

Answer: Degree of cure; Degree of conversion; Light transmittance; Light transmission; Polymerisation kinetics; Resin based luting composite; Indirect restorative materials; Lucirin-TPO; Irradiation time; Camphorquinone

Query: Please check the hierarchy of the section headings and correct if necessary.

Answer: Ok

Query: This opening parenthesis does not have a corresponding closing parenthesis. Please insert the parenthesis in the appropriate position.

Answer: Please close the parenthesis after (e.g. Ref. 36)

Query: Please provide the volume number and page range in Refs. [6,7].

Answer: Ref 6: The article was still in Press but now I can have the complete reference: J Prosthet Dent 2018, Volume 119, Issue 5, May 2018, Pages 743-748.e1

Query: Please check the edit made in Ref. [7], and correct if necessary.

Answer: Ok

Query: Please note that two sets of figure caption were provided. One in the manuscript and one in a separate file named "Figure captions.docx". We have used the one provided in the manuscript. Kindly check and correct if necessary.

Answer: The reference to the "B" is missing: please add "(B)" at the second line, after "irradiated with BluePhaseG2 (Ivoclar-Vivadent)"

Query: This closing parenthesis does not have a corresponding opening parenthesis. Please insert the parenthesis in the appropriate position.

Answer: Please remove the parenthesis after mW/cm², and the corresponding parenthesis are "(" before mW/cm² and ")" after 0,1

Query: Please check the presentation of all the Tables and correct if necessary.

Answer: The first table is incomplete; The other tables could take less space (see the document attached Tables.docx please), and there is a line not needed in the middle of the table 3

Attachments: Tables.docx